

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			Heterogeneous
Total thickness	EN ISO 24346	mm	2,0
Wear layer thickness	EN ISO 24340	mm	0,9
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	m	20
Total weight	EN ISO 23997	kg/m2	2,6
CLASSIFICATION			
Product specification	EN 649		✓
European classification	EN 685	class	34/43
Residential indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max. %	0,2
Light fastness	EN 20105 B02	grade	6
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Fire resistance	EN 13501-1	class	Cfl-s1
	BS 476		Class 1
	Gost 30402-94		G1
Slip resistance	DIN 51130		R10
	DIN 51097		C
	AS/NZS 4586:2004		R11
Abrasion resistance	ISO 9352	g/1000 circle	-0,25
Bacterial resistance	EN ISO846:1999		✓
Castor chair resistance	EN 425		✓
Surface treatment			CLP
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
Seaming method			heat or cold weld
Warranty		year	10
CE MARKING	EN 14041		✓