




Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			compact heterogeneous
Total thickness	EN ISO 24346	mm	2
Wear layer thickness	EN ISO 24340	mm	0,7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m ²	2,7
CLASSIFICATION			
Product specification	EN 649		✓
European classification	EN 685	class	34/43
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max. %	0,2
Light fastness	EN ISO 105-B02	grade	6
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Fire resistance	EN 13501-1	class	Bfl-s1
	ASTM E 648/662	class	Class 1 / pass
	Gost 30402-94	class	G1
	DIN 4102 / ÖNORM	class	B1
Slip resistance	DIN 51130		R10
	ASTM D2047-99		dry: 0,92 / wet: 0,84
Abrasion resistance	ASTM D3884-01	g/1000 circle	-0,19
	ISO 9352	g/1000 circle	-0,25
Shore A hardness	ISO 868		90
Chemical resistance	EN ISO26987		✓
	ASTM F925-02		✓
Bacterial resistance	EN ISO846:1999		✓
Castor chair resistance	EN 425		✓
Surface treatment			CLP
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
Seaming method			heat or cold weld
Warranty		year	7
CE MARKING	EN 14041		✓